

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 : C07H 1/00, 15/04		A1	(11) International Publication Number: WO 94/14823
			(43) International Publication Date: 7 July 1994 (07.07.94)
(21) International Application Number: PCT/US93/12556		(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 20 December 1993 (20.12.93)			
(30) Priority Data: 07/995,748 21 December 1992 (21.12.92) US			
(71) Applicant: UNIVERSITY OF IOWA RESEARCH FOUNDATION [US/US]; 214 Technology Innovation Center, Oakdale Research Campus, Oakdale, IA 52319 (US).		Published With international search report.	
(72) Inventors: DORDICK, Jonathan, S.; 2996 Walnut Ridge Lane, Iowa City, IA 52240 (US). MARTIN, Brett, D.; Apartment 24C, 945 Oakcrest, Iowa City, IA 52246 (US). LINHARDT, Robert, J.; 1422 Plum Street, Iowa City, IA 52240 (US).			
(74) Agent: GABRIC, Ralph, J.; William, Brinks, Hofer, Gilson & Lione, NBC Tower, Suite 3600, 455 North Cityfront Plaza Drive, Chicago, IL 60611 (US).			
(54) Title: SUGAR-BASED POLYMERS			
(57) Abstract			
<p>Sugar-containing poly(acrylate)-based hydrogels and methods of preparing these hydrogels are disclosed. Poly(sugar acrylate)s are chemoenzymatically prepared and crosslinked to form hydrogels, which are water absorbant.</p>			
<p>BEST AVAILABLE COPY</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

5

SUGAR-BASED POLYMERS

10 This application is a Continuation-in-Part of
Application Serial No. 706,929, filed May 28, 1991,
which is a Continuation-in-Part of Application Serial
No. 521,076, filed May 8, 1990.

BACKGROUND OF THE INVENTION

15 The present invention is directed to novel
sugar-based polymers and novel methods of making these
sugar-based polymers. In copending application Serial
No. 521,076, incorporated herein by reference,
Applicants disclose a method of manufacturing sugar-
based polymers using biological catalysts (enzymes).
20 Enzymes are very regioselective, thereby allowing the
synthesis of acylated sugars useful in the synthesis of
sugar-based polymers of the present invention.
Applicants' copending application discloses,
inter alia, methods of regioselectively diacylating
25 sugar molecules with an organic acid derivative having
at least two carboxyl functionalities. These
diacylated sugars are then polymerized to form a
polymer having repeating sugar units in the polymer
backbone.

30 Applicants have discovered that sugar-based
polymers can be manufactured by first using enzymatic
synthesis in the regioselective step of manufacturing
the diacylated sugar intermediates useful in the
manufacture of sugar-based polymers. Subsequently,


- 2 -

chemical methods can be used to polymerize the diacyl-
 ated sugar intermediates. The use of both enzymatic
 and chemical synthesis is known as chemoenzymatic
 synthesis. The use of chemoenzymatic methods of making
 5 sugar-based polymers permits one to take advantage of
 the regioselectively associated with enzymatic
 synthesis while simultaneously taking advantage of the
 speed associated with chemical synthesis.

SUMMARY OF THE INVENTION

The present invention is directed to novel
 methods of making sugar-based polymers, as well as
 novel sugar-based polymers.

In one aspect of the present invention, a
 15 method of preparing a sugar-based polymer hydrogel is
 provided. An amount of concentrated acylated sugar is
 provided having the structure:



wherein S is selected from the group consisting of
 sucrose acylated at the 1'- position, raffinose at the
 1"-position, fructose at the 1-position, trehalose at
 25 the 6-position, α - and β -phenyl- or alkylglucosides at
 the 6-position, α - and β -haloglucosides at the 6-
 position, α - and β -phenyl or alkylgalactosides at the
 6-position, α - and β -halogalactosides at the 6-
 position, α - and β -phenyl- or alkymannosides at the 6-
 30 position, α - and β -halomannosides at the 6-position,
 and mixtures thereof; R is selected from the group
 consisting of hydrogen, straight chain alkanes having
 from about 1-10 carbon atoms, and mixtures thereof.
 The concentrated acylated sugar is heated to greater
 35 than about 60°C to permit the acylatd sugar to
 autopolymerize and form a hydrogel.

In another aspect of this invention, an
 amount of free-radical polymerization initiator and an
 amount of cross-linking agent are mixing with the

- 3 -

acylated sugar. The acylated sugar is then permitted to polymerize to form a hydrogel.

5 DETAILED DESCRIPTION OF THE
PREFERRED EMBODIMENTS

10 The present invention is directed to novel polymers which incorporate an abundant, relatively inexpensive and recyclable resource, sugar. The present invention is also directed to novel methods of making these polymers. It is contemplated that the sugar-based polymers of the present invention will find significant use in diaper liners as well as in other absorbent materials, packaging materials, drug delivery polymers, and in a variety of other commercial applications.

15 The sugar-based polymers of the present invention are manufactured pursuant to a combination of enzymatic and chemical synthesis (i.e. chemoenzymatic synthesis). In particular, hydrolytic enzymes are used to regioselectively acylate sugar molecules with organic acid derivatives. The acylated sugar intermediates are then polymerized via chemical methods.

20 The present invention contemplates the utilization of mono-, di-, tri- and oligosaccharides. Preferred sugars are glucose, mannose, fructose (monosaccharides); sucrose, lactose, maltose, trehalose (disaccharides); and raffinose (a trisaccharide). More preferred sugars for use in the present invention include sucrose, fructose, raffinose, lactose, maltose and trehalose. Even more preferred sugars, however, are fructose, sucrose and raffinose. The most preferred sugar is sucrose.


35 COPOLYMERIZATION OF A COREACTANT WITH SUGAR
DIACYLATED WITH ORGANIC ACID DERIVATIVES
HAVING TWO CARBOXYL FUNCTIONALITIES

In a preferred embodiment of the present invention, diacylated sugar intermediates are made by

- 4 -

mixing sugar and organic acid derivatives having at least two carboxyl functionalities. The sugar is regioselectively diacylated with the organic acid derivatives pursuant to the use of hydrolytic enzymes.

Any organic acid derivative having at least two carboxyl functionalities is contemplated for use in the present invention. Preferably, the organic acid derivative will comprise a diacid of the general formula:



wherein R_1 and R_3 are selected from the group consisting of leaving groups and R_2 is any moiety which will not interfere with the acylation of the sugar and/or subsequent polymerization of the resulting acylated sugars.

For example, R_2 could be selected from the group consisting of alkanes, branched alkanes, alkenes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and mixtures thereof. Again, the only critical limitation with respect to R_2 is that it not contain a reacting functionality (as, for example, a hydroxyl, an amine and/or a carboxyl group) which would substantially interfere with the acylation, and/or subsequent polymerization, of the sugar.

As previously stated, R_1 and R_3 are leaving groups. By leaving group, it is meant that R_1 and R_3 may be any group that is replaced by sugar in the presence of a hydrolytic enzyme. Preferably, R_1 and R_3 are leaving groups that are poorer nucleophiles than the sugar. This is preferred because, as presently understood, the sugar molecules replace R_1 and R_3 on the organic acid derivatives by an enzyme-organic acid derivative intermediate via a nucleophilic mechanism. Where R_1 and R_3 are poorer nucleophiles than the sugar,

- 5 -

there will be little competition between these groups and the sugar molecules, thus resulting in a greater yield of diacylated sugar intermediates than if R_1 and R_3 were good nucleophiles relative to sugar.

5 Preferably, R_1 and R_3 are activated leaving groups selected from the group consisting of mono-, di-, and trifluoro ethanol; mono-, di-, and trichloroethanol; halogens; and enol esters. Most preferred organic acid derivatives contemplated for use in the present
10 invention are bis(2,2,2-trifluoroethyl) adipate, vinyl adipate and isopropenyl adipate.

It should be noted that the properties desired of the final sugar-based polymer may be considered when selecting organic acid derivatives. For
15 example, the R_2 group of the afore-described organic acid derivative will ultimately be incorporated into the backbone of the sugar-based polymer. Thus, the properties of the sugar-based polymer will be effected by the nature of this R_2 group. Longer R_2 groups will
20 result in a polymer having longer hydrocarbon links. Such a polymer will have increased flexibility and increased hydrophobicity. Accordingly, where hydrophobicity and/or flexibility is desired, R_2 will be selected from the group consisting of alkanes, alkenes
25 and substituted alkenes having about ten or more carbons. Conversely, shorter hydrocarbon links will likely increase the hydrophilicity and rigidity of the resulting sugar-based polymer. Thus, where hydrophilicity and/or rigidity is desired, R_2 will be
30 selected from the group consisting of alkanes, alkenes, substituted alkenes, aromatic moieties and substituted aromatic moieties having less than about 10 carbons.

Alternately, if an ionic sugar-based polymer is desired, R_2 can be, for example, selected from the
35 group consisting of free acids or salts (particularly sodium or potassium salts) containing SO_3^- , NO_3^- and PO_4^{3-} . The incorporation of such charged R_2 groups into

- 6 -

the sugar-based polymers may render these polymers useful as flocculents for use in, for example, water treatment applications.

5 In some cases, a highly crystalline sugar-based polymer may be desired as, for example, where the polymer is contemplated for use as a thermoplastic material. Crystallinity can be enhanced by regularity in the polymer backbone and by increasing the polarity of the polymer. This can be achieved by using organic
10 acids having identical polar R_2 groups. However, for other uses (e.g., clear plastic packaging films) a non-crystalline polymer is preferred. To decrease the crystallinity of the sugar-based polymer two approaches can be used. First, to disrupt the regularity of the
15 polymer (and, thus, decrease crystallinity) organic acid derivatives having two different linkage lengths (i.e. different R_2 groups) may be employed in a single synthesis of the sugar-based polymer. This should result in a random copolymer (i.e., the two lengths
20 should be randomly distributed in the polymer chain, thereby decreasing regularity). The second approach is to decrease the polarity of the sugar-based polymer by using longer, more hydrophobic R_2 groups in the organic acid derivative. As the polarity decreases, the
25 crystallinity may decrease.


As can be discerned from the preceding discussion, by varying the character of the R_2 group in the organic acid derivatives, the properties of the resulting sugar-based polymer may be controlled. The
30 only practical limitations on the nature of the R_2 group are that it should be soluble in the substantially non-aqueous organic solvent and not substantially interfere with the acylation of the sugar and subsequent polymerization of the acylated sugars.

35 The sugar molecules must be acylated in at least two locations in order to synthesize the sugar-based polymers of the present invention. Most

- 7 -

preferably, the sugar molecules will be acylated at only two locations (i.e. diacylated). If, however, certain properties were desired (i.e. greater cross-linking, hydrophobicity, less absorbency) the sugar molecules may be acylated at more than two hydroxyl positions. In any event, the amount of organic diacid derivative to sugar should be at least a 1:1 molar ratio. Where a tri-, tetra-, or higher acid derivative is used as the acyl donor, the ratio of the organic acid derivative to sucrose should be adjusted according to the aforesaid ratio (i.e. a tetra acid derivative should be present in a 2:1 molar ratio to sugar). Preferably, the organic acid derivative is present in excess when mixed with the sugar.

The sugar is diacylated with the organic acid derivative via the use of hydrolytic enzymes. Hydrolytic enzymes are highly selective biological catalysts that typically operate under mild reaction conditions (e.g., ambient temperatures and pressures, neutral solutions, etc.). Hydrolytic enzymes include lipases, esterases, proteases, and carbohydrases. In an aqueous environment, hydrolytic enzymes are capable of catalyzing both hydrolysis and ester formation according to the following reversible equation:



In aqueous systems, the large concentration of water (ca. 55 M) results in a low equilibrium yield of ester. Thus, although lipases and esterases have been employed to synthesize sugar esters of fatty acids in aqueous solutions, low yields of the sugar esters are achieved due to the hydrolysis of the product in the aqueous solution. However, the use of enzymes in substantially non-aqueous organic solvents dramatically increases the yield of acylated sugar (i.e. the ester product in the above equation). Therefore, to increase the yield of

- 8 -

acylated sugar, and ultimately the yield of final polymer product, it is preferred that the sugars are acylated in a substantially non-aqueous organic solvent. Unfortunately, however, sugars are soluble in only a few substantially non-aqueous organic solvents. Additionally, most hydrolytic enzymes lose their activity in the few substantially non-aqueous organic solvents capable of solubilizing sugars.

According to the present invention, substantially non-aqueous organic solvents are screened for their ability to solubilize sugar and organic acid derivatives, as well as for their effect on the catalytic activity of various hydrolytic enzymes. Once having determined the compatibility of various sugars, hydrolytic enzymes and substantially non-aqueous organic solvents, the diacylated sugar intermediates may be made.

Hydrolytic enzymes initiate the regioselective diacylation of the sugar molecules with organic acid derivatives having two carboxyl functionalities. Several hydrolytic enzymes have been found to retain their catalytic activity in either pyridine or dimethylformamide. Applicants have ascertained that the following hydrolytic enzymes are catalytically active in pyridine: Aminoacylase; Lipozyme, available from NOVO CHEMICAL; Fungal Amylase, available under the trade name "HT" from MILES KALICHEMIE; Bacterial protease, available under the trade name "Bioenzyme" from GIST-BROCADES; Amylase from Bacillus subtilis available under the trade name "Rapidase" from GIST-BROCADES; Alkaline protease, available under the trade name "Proleather" from AMANO; Bacillus protease available under the trade name "Protease N" from AMANO; Lipase from Candida cylindracea, available from SIGMA; Lipase from porcine pancreas, available from SIGMA; and Lipase from Penicillium Sp., available under the trade name "Lipase

- 9 -

G" from AMANO. Additionally, Applicants have determined that subtilisin is catalytically active in dimethylformamide. Both highly purified or crude subtilisin are catalytically active; however, the substantially less expensive crude subtilisin is preferred. Although specific to the substantially non-aqueous organic solvent, it should be noted that, as presently understood, the hydrolytic enzymes are non-specific to the organic acid derivative.

The diacylation of the sugar molecules is conducted in a substantially non-aqueous organic solvent capable of solubilizing both the sugar and the organic acid derivative (at least about 10 mmol of sugar/l liter of solvent, and preferably greater than about 100 mmol sugar/l liter of solvent). If the solubility of the sugar and organic acid derivative is substantially less than about 10 mmol/l liter solvent, the manufacture of the polymers of the present invention may not be economically desirable. Sugars are reasonably soluble in only a few, very hydrophilic, substantially non-aqueous organic solvents such as pyridine, dimethylformamide morpholine, N-methylpyrrolidone and dimethylsulfoxide. Care should be taken, however, in selecting an appropriate organic solvent in that the organic solvent should be screened to assure that it does not significantly detract from the catalytic activity of the hydrolytic enzyme. Additionally, the substantially non-aqueous organic solvent should not hydrolyze the diacylated sugar intermediates (i.e. the products of the diacylation of the sugar molecules with the organic acid derivative). Of the previously mentioned organic solvents, pyridine and dimethylformamide are the preferred substantially non-aqueous organic solvents for use in the acylation of sugar molecules. The most preferred organic solvent, however, is pyridine. Pyridine is most preferred because it solubilizes a broader range of

- 10 -

sugars than other solvents tested to date, without substantially detracting from the activity of various hydrolytic enzymes.

Where pyridine is used, the presently preferred enzymes for the diacylation of the sugar molecules are alkaline protease, Bacterial protease, Bacillus protease, and aminocyclase. At present, the most preferred hydrolytic enzyme in pyridine is activated alkaline protease. The alkaline protease is activated by dissolving the enzyme in about 20 mmol per liter sodium borate buffer at a pH of about 9.5, and dialyzing the resulting mixture against added buffer. Thereafter, the dialyzed protein is freeze dried. However, where dimethylformamide is the organic solvent selected, the presently preferred enzyme is subtilisin.


The amount of hydrolytic enzyme provided to catalyze the regioselective diacylation of the sugar molecules is not critical, provided there is sufficient enzyme to initiate the diacylation of the sugars (about 10 mg/ml). By varying the amount of enzyme employed, however, the speed of the acylation can be affected. In general, increasing the amount of hydrolytic enzyme increases the speed at which the sugar is acylated.

The sugar is diacylated by mixing the sugar, organic acid derivative and hydrolytic enzyme in the substantially non-aqueous organic solvent. The amount of hydrolytic enzyme should be sufficient to catalyze the regioselective acylation of the sugar molecules with the organic acid derivative. The amount of the organic acid derivative and sugar in the aforesaid mixture should be at least about 1:1 molar ratio. Preferably, however, the organic acid derivative will be mixed in excess. The aforesaid ingredients may be mixed in a substantially non-aqueous solvent as previously described according to any method known by those skilled in the art.

- 11 -

Preferably, however, the aforesaid mixture is agitated at about 100-300 rpms in an orbital shaker at a temperature of from about 10°C to about 60°C for a period of time sufficient to permit the diacylation of the sugar molecules. A suitable time period, for example, is about 12-48 hours. The longer the mixture is agitated, however, the higher the yield of diacylated sugar. The temperatures should not substantially exceed 60°C because the hydrolytic enzyme may lose its activity. Any method of agitation known by those skilled in the art is contemplated by the present invention, as for example, magnetic stirring or overhead mechanical stirring. Once the sugar molecules have been diacylated, they are separated from the mixture. Any method of separation known by those skilled in the art is suitable, as, for example, silica gel chromatography.

Where the sugar is diacylated with an organic diacid derivative, the resulting sugar intermediate will have the general formula:



For purposes of clarity, the organic acid derivative's contribution to the above structure is bracketed. With reference to the above formula, S comprises sugar, and R and R' are R₁ or R₃ from the organic acid derivatives. In particular, R and R' are R₁ or R₃ on the end opposite the portion of the organic acid derivative that is replaced by the sugar molecule. Finally, R₂ and R₂' are, of course, from the R₂ portion of the organic acid derivatives. Clearly, R, R', R₂ and R₂' are as previously discussed with respect to the organic

- 12 -

acid derivative. Thus, R' and R are leaving groups that are preferably poorer nucleophiles than sugar. Preferably, R and R' are selected from the group consisting of mono-, di- and trifluoroethanols; mono-,
5 di- and trichloroethanols; halogens; enol esters and mixtures thereof. R₂ and R₂' are selected from the group consisting of alkanes, branched alkanes, alkenes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and
10 mixtures thereof.

With regard to the aforesaid structure, the sugars are diacylated at primary hydroxyl positions. For example, sucrose is acylated at the 6- and 1'-
15 positions, fructose at the 1- and 6- positions, raffinose at the 6- and 1"- positions, lactose at the 6- and 6'- positions, maltose at the 6- and 6'- positions, and trehalose at the 6- and 6'- positions.


The diacylated sugars are useful intermediates in the manufacture of sugar-based
20 polymers. Particularly, these diacylated sugar intermediates may be copolymerized with various coreactants thereby yielding a sugar-based polymer. The copolymerization should be conducted in a solvent in which the diacylated sugars and coreactant are
25 soluble. Furthermore, the solvent should not substantially impair the coreactant's ability to take part in the copolymerization nor should it deacylate the diacylated sugar intermediates to a substantial extent. Suitable solvents include any polar solvent with a
30 dielectric constant greater than about 10 as, for example, dimethylformamide, N-methylpyrrolidone, dimethylsulfoxide and dimethyl acetamide.

As used herein, a coreactant is any compound that will take part in a copolymerization with the
35 diacylated sugar intermediates. With reference to the afore-indicated structure of the diacylated sugar intermediate, the coreactant will react with the R' and

- 13 -

R groups of the diacylated sugar intermediate. Thus, by utilizing a coreactant with two functionalities per molecule that are capable of reacting with the R and R' groups of the diacylated sugars, the diacylated sugars can be copolymerized having coreactant linkages.

Suitable coreactants include but are not necessarily limited to diamines, dithiols, diacids and mixtures thereof. Preferably, the coreactant will be a compound having the general formula



wherein X is selected from the group consisting of -NH₂, -SH, -COOH and mixtures thereof; and R is selected from the group consisting of alkanes, branched alkanes, alkenes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and mixtures thereof.

As with the R₁ and R₁' groups of the organic acid derivatives, the R group of the coreactant will be incorporated into the final polymer product (it will link the diacylated sugars). Accordingly, the selection of the R group of the coreactant may be based on the properties desired of the final sugar-based polymer product. The factors previously discussed with respect to the nature of the R₁ group of the organic acid derivative apply as well to the R group of the coreactant.


More preferably, the coreactant is selected from the group consisting of aliphatic diamines and aromatic diamines. Most preferably, the coreactant will be selected from the group consisting of aliphatic diamines having 2-6 carbon atoms. The preference for these diamines is based on their commercial availability and relatively low cost.

The copolymerization of the diacylated sugars and coreactant is carried out by mixing the diacylated sugars, coreactant and a solvent as previously discussed and agitating this mixture for a period of

- 14 -

time sufficient to permit the copolymerization of the diacylated sugars with the coreactant (about 24 hours). The diacylated sugar intermediate and coreactant are mixed in at least a 1:1 molar ratio. Preferably, the aforesaid mixture will be mixed at 250 rpms at 25°C in an orbital shaker. Of course, any method of mixing and agitation known in the art are contemplated for use in the present embodiment. The resulting sugar based polymer is recovered by evaporating off the solvent by any suitable method known by those skilled in the art. The final sugar-based polymer product may then be washed with, for example, acetone and dried under vacuum.

The aforesaid method yields a sugar-based polymer having the general formula:




wherein S comprises sugar, R₂ and R', are selected from the group consisting of alkanes, branched alkanes, alkenes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and mixtures thereof; A is the coreactant; and n is a number greater than 1. With reference to the above formula, the sugars are linked at two primary hydroxyl positions. For example, sucrose is linked at the 6- and 1'- positions, fructose at the 1- and 6- positions, raffinose at the 6- and 1"- positions, lactose at the 6- and 6'- positions, maltose at the 6- and 6'- positions, and trehalose at the 6- and 6'- positions.

- 15 -

COPOLYMERIZATION OF A COREACTANT WITH SUGAR
DIACYLATED WITH ORGANIC MONO-ACID DERIVATIVES

In another preferred embodiment of the present invention, the sugar may be diacylated as previously discussed with organic mono-acid derivatives that have been specifically tailored to react with the coreactant. The organic acid derivatives will have at least one reactive functionality. By reactive functionality it is meant that the organic acid derivative has a functionality capable of reacting with a functionality on the coreactant. Thus, the acylated sugars will be capable of reacting with the coreactant. The coreactant will have at least two functionalities capable of reacting with the acylated sugars. The acylated sugars and coreactant are then copolymerized by mixing the acylated sugar and coreactant whereby a functionality on the coreactant reacts with an acylated sugar and at least one other functionality on the coreactant reacts with another acylated sugar. The resulting polymer will comprise of acylated sugars linked via the coreactant.


The resulting sugar based polymer will have the general formula




wherein S comprises sugar; A is selected from the group consisting of coreactants having at least two functionalities wherein a functionality on the coreactant has reacted with an acylated sugar and at least one other functionality on the coreactant has reacted with another acylated sugar; and n is a number greater than 1.

- 16 -

According to this embodiment, a sugar is diacylated as previously discussed with an organic acid derivative having the general formula:



wherein R_1 is a leaving group as previously discussed and R is specifically selected such that it contains a functionality that will react with the coreactant. The resulting diacylated sugar will have the general formula:



wherein S comprises sugar, and R and R' are selected such that they contain a functionality that will react with functionalities on the coreactant to yield a copolymer of acylated sugar moieties linked via the coreactants.

With reference to the above structure, sucrose is acylated at the 6- and 1'- positions, fructose at the 1- and 6- positions, raffinose at the 6- and 1"- positions, lactose at the 6- and 6'- positions, maltose at the 6- and 6'- positions, and trehalose at the 6- and 6' positions.


For example, R and R' can be selected from the group consisting of terminally double bonded compounds having the general formula: $-\text{RC} = \text{CH}_2$, wherein R is selected from the group consisting of hydrogen, alkanes, alkenes, branched alkenes, substituted alkenes, aromatic moieties, substituted aromatic moieties and mixtures thereof.

Where R' and R are compounds having terminal double bonds, the diacylated sugar may be copolymerized with a coreactant selected from the group consisting of

- 17 -

dithiols, diamines, diiodides, diacids and mixtures thereof.

The resulting sugar-based polymer will have the general formula:




wherein S comprises sugar; R is selected from the group consisting of hydrogen, alkanes, alkenes, branched alkanes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and mixtures thereof; A is a coreactant selected from the group consisting of dithiols, diamines, diiodides, diacids and mixtures thereof; and n is a number greater than 1.

With reference to the above structure, sucrose is acylated at the 6- and 1'- positions, fructose at the 1- and 6- positions, raffinose at the 6- and 1" positions, lactose at the 6- and 6'- positions, maltose at the 6- and 6'- positions, trehalose at the 6- and 6'- positions and mixtures thereof.

Alternatively, a diacylated sugar is provided having the previously indicated formula wherein R and R' are selected from the group consisting of alkyl halides having the general formula -RCHX, wherein X is a halide and preferably selected from the group consisting of chloride and bromide, and R is selected from the group consisting of hydrogen, alkanes, alkenes, branched alkanes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and mixtures thereof; Preferably R is a methyl. These diacylated sugars may

- 18 -


be copolymerized with a coreactant selected from the group consisting of diols. The resulting sugar-based polymer will have the general formula:



wherein S comprises sugar, R is selected from the group consisting of hydrogen, alkanes, alkenes, branched alkanes, substituted aliphatic moieties, substituted alkenes, aromatic moieties, substituted aromatic moieties and mixtures thereof; A comprises a diol; and n is a number greater than 1.

POLYMERIZING ALKYLATED SUGARS WITH ORGANIC ACID DERIVATIVES

In another preferred embodiment of the present invention, a method of polymerizing alkylated sugars is provided. Two primary hydroxyl positions are first blocked by diacylating the sugar with any compound having an ester group (hereinafter referred to as a blocking compound) capable of undergoing a transesterification reaction with a primary hydroxyl group on the sugar molecule. The blocking compounds are identified as such because the blocking compounds acylate the sugar at two primary hydroxyl sites thereby blocking these two sites from the subsequent alkylation of the other (unblocked) hydroxyl groups. Suitable blocking compounds have the general formula:



wherein R is selected from the group consisting of alkanes, alkenes, branched alkanes, substituted alkenes, aromatic moieties, substituted aromatic moieties, substituted aliphatic moieties and mixtures

- 19 -

thereof; and R' is selected from the group consisting of leaving groups.

It is presently believed that the sugar molecules are acylated with the blocking compound at two primary hydroxyl positions pursuant to the nucleophilic mechanism previously discussed with respect to the diacylation of sugar with the organic acid derivatives. Accordingly, R' is preferably a poorer nucleophile than sugar. Most preferably, R' is selected from the group consisting of mono-, di-, and trifluoro ethanols; mono-, di- and trichloroethanols; halogens and enol esters.

A most preferred blocking compound is vinyl acetate.

The sugar is diacylated with the blocking compounds in a manner similar to the previously discussed diacylation of sugar with the organic acid derivatives. In particular, the sugar is acylated at two primary hydroxyl positions in a substantially non-aqueous organic solvent capable of solubilizing both the sugar and blocking compounds as, for example, pyridine, dimethylformamide, morpholine, N-methylpyrrolidone and dimethylsulfoxide. A hydrolytic enzyme is used to catalyze the diacylation of the sugar molecules with the blocking agent. Preferably, the diacylation will be carried out in pyridine in the presence of a hydrolytic enzyme selected from the group consisting of activated alkaline protease, Bacterial protease, Bacillus protease, aminoacylase and lipase P-30 from Amano. More preferably, the diacylation of sugar with the blocking compounds will be performed in pyridine in the presence of activated alkaline protease. Alternately, the diacylation of the sugar with blocking compounds can be performed in dimethylformamide in the presence of subtilisin.

The sugar is diacylated by mixing at least a 2:1 molar ratio of blocking compounds to sugar.

- 20 -

Preferably, an excess of blocking compound will be mixed with the sugar. The resulting mixture is preferably agitated at about 250 rpms at 40°C in pyridine for a time sufficient to permit the di-

5 acylation of the sugar (preferably about 24 hours).

Once the sugar has been diacylated (i.e., acylated at two primary hydroxyl positions) with the blocking compounds, it is mixed with an excess of an alkylating agent in the presence of a catalyst. Any

10 and all alkylating agents and catalysts known by those skilled in the art for alkylating the open hydroxyl positions are contemplated for use in the present invention. The alkylating agent must be capable of alkylating the free hydroxyl position, without

15 deacylating the blocking compounds.

Suitable alkylating agents include, but are not necessarily limited to the alkyl halides and diazalkanes. Preferred alkylating agents are the alkyl halides having less than about 5 carbons. The

20 most preferred alkylating agent is methyl iodide.

Catalyst contemplated for use in alkylating the diacylated sugars include, but are not necessarily limited to non-nucleophilic bases such as trialkyl-

25 amines, dialkyl amino pyridines, dimethylaminopyridine and silver oxide. The preferred catalyst is dimethylaminopyridine.

The diacylated sugar is preferably alkylated by mixing the sugar, alkylating agent and catalyst in pyridine.

After alkylating the hydroxyl sites on the sugar, the alkylated sugar is deacylated by mixing the sugar with an excess of base (preferably aqueous sodium hydroxide having 20-30% water) at about 250 rpms and

30 room temperature (25°C) for about 24 hours to deblock the two primary hydroxyl positions. Alternately, the alkylated sugar may be deacylated by mixing (about 250


35 rpms) the sugar with an excess of sodium methoxide in

- 21 -

methanol for about one hour at ambient temperature (about 25°C).

After deacylation, the resulting sugar has two open primary hydroxyl positions, the remaining hydroxyl positions having been alkylated. This alkylated sugar is then mixed with an organic acid derivative in the presence of a chemical catalyst in a substantially non-aqueous organic solvent. The solvent is selected such that the organic acid derivative and alkylated sugar are soluble and catalyst active.

The organic acid derivative can be selected as previously discussed. In general, the organic acid derivative will have the general formula:




wherein R_1 and R_3 are leaving groups as previously discussed, and R_2 is any moiety which, as previously discussed, will not interfere with the acylation and subsequent polymerization of the sugar. As it will ultimately be incorporated in the sugar-based polymer, R_2 may be selected as previously discussed depending on the properties desired of the final sugar-based polymer. Similarly, R_1 and R_3 are selected as previously discussed. In this particular embodiment, however, the preferred organic acid derivatives are the adipoyl halides. More preferred are the succinyl halides, the malonyl halides, sebacoyl halides and the adipoyl halides. Even more preferred are adipoyl chloride, succinyl chloride, malonyl chloride and sebacoyl chloride. Adipoyl chloride is the most preferred organic acid derivative.

The alkylated sugar and organic acid derivative must be mixed in a 1:1 molar ratio. The alkylated sugar, organic acid derivative, catalyst and solvent are mixed (250 rpm) at ambient temperature (25°C) for a time sufficient to permit the sugar and organic acid derivative to polymerize (about 1 hour). Thereafter,

- 22 -

the sugar-based polymer may optionally be dealkylated according to any method known by those skilled in the art.

The resulting sugar-based polymer has the general formula:



wherein S comprises sugar; R_2 is selected from the group consisting of alkanes, branched alkanes, alkenes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and mixtures thereof; and n is a number greater than 1.

With reference to the above structure, the sugars are linked at two primary hydroxyl positions. For example, sucrose is linked at the 6- and 1'-positions, fructose at the 1- and 6-positions, raffinose at the 6- and 1"-positions, lactose at the 6- and 6'-positions, maltose at the 6- and 6'-positions, and trehalose at the 6- and 6'-positions.

POLYMERIZING ALKYLATED SUGARS AND A DIISOCYANATE

In yet another preferred embodiment of the present invention, a diisocyanate can be used in place of the acyl halide. Specifically, an alkylated sugar having two open primary hydroxyl groups is provided as previously discussed. The alkylated sugar is mixed with a diisocyanate of the general formula:




wherein R is selected from the group consisting of alkanes, alkenes, branched alkanes, substituted alkenes, aromatic moieties, substituted aliphatic

- 23 -

moieties, substituted aromatic moieties and mixtures thereof. Because R will be incorporated into the final polymer product, it can be selected with the desired properties of the polymer in mind. Accordingly, R may be selected in the manner previously discussed with regard to the R₂ group of the organic acid derivative. A preferred diisocyanate is 1,6-hexamethylene diisocyanate.

The alkylated sugar and diisocyanate are mixed in a 1:1 molar ratio in dimethylformamide in the presence of a trialkyl amine catalyst (preferably triethylamine) for a time sufficient to permit the polymerization of the alkylated sugar and the diisocyanate (about 24 hours).

The resulting sugar-based polymer will have the general formula:



wherein S comprises sugar; R is selected from the group consisting of alkanes, alkenes, branched alkanes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and mixtures thereof, and n is a number greater than one.

With reference to the above structure, sucrose is linked at the 6- and 1'- positions, fructose at the 1- and 6- positions, raffinose at the 6- and 1"- positions, lactose at the 6- and 6'- positions, maltose at 6- and 6'- positions and trehalose at the 6- and 6'- positions.


PREPARATION OF POLY(SUGAR ACRYLATES)

In yet another preferred embodiment of the present invention, a method of manufacturing a sugar-based polymer is provided. Mono-, di-, tri- and oligosaccharides that are non-reducing sugars are

- 24 -

contemplated for use in the present embodiment. Any reducing monosaccharide, however, can be converted to a non-reducing sugar by either alkylating or halogenating the 1-position. Preferably, the sugar is selected from the group consisting of α - and β - alkylglucosides, α - and β - haloglucosides, α - and β - alkylgalactosides, α - and β - halogalactosides, α - and β - alkylmannosides, α - and β - halomannosides, sucrose, fructose, mannose, trehalose and raffinose. Preferred sugars are α - and β - methylglucoside, α - and β - methyl galactoside, α - and β - methylmannoside, sucrose, fructose, mannose, trehalose and raffinose. More preferred sugars are sucrose, fructose and raffinose. The most preferred sugar is sucrose.

Specifically, a sugar is first acylated with an acylating compound having the general formula:



wherein R is selected from the group consisting of hydrogen, alkanes, alkenes, branched alkanes, substituted alkenes, substituted aliphatic moieties, aromatic moieties, substituted aromatic moieties and mixtures thereof, and R' is a leaving group. Again, it is presently believed that the sugar is acylated with the acylating compound pursuant to a nucleophilic mechanism as previously discussed. Accordingly, R' is preferably a good leaving group as previously discussed with regard to R₁ and R₂ of the organic acid derivative.

A preferred acylating compound is vinyl acrylate.

The sugar is acylated by mixing the sugar and acylating compound in a substantially non-aqueous, organic solvent. The solvent is selected such that the sugar and acylating compound are soluble (i.e., at least about 10 mmol/liter and preferably about 100 mmol/liter) and the hydrolytic enzyme is active.

- 25 -


Suitable solvents include anhydrous pyridine and dimethylformamide. Anhydrous pyridine is the preferred solvent.

The hydrolytic enzymes useful for the acylation of the sugar are the same as those disclosed previously. Additionally, lipase P-30 from Pseudomonas sp. available from AMANO has been found suitable. Preferably, activated alkaline protease from Bacillus sp. will be used.

Preferably, the sugar is acylated in the presence of a compound selected to inhibit the premature polymerization of the acylating compound. Suitable inhibitors include ascorbate and hydroquinone. Hydroquinone is preferred. Of course, other inhibitors known by those skilled in the art may be used.

The sugar and acylating compound are mixed in the presence of hydrolytic enzyme and inhibitor in the solvent at a temperature of about 10°C to about 60°C for a time sufficient to permit the acylation of the sugars (preferably about 24 hours). The sugar and acylating compound are mixed in at least a 1:1 molar ratio, with an excess of acylating compound being preferred. Once formed, the acylated sugars may be separated pursuant to silica gel chromatography or any other method of separation known by those skilled in the art.

The resulting acylated sugars have the general formula:



wherein S comprises sugar, and R is selected from the group consisting of hydrogen, alkanes, alkenes, branched alkanes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and mixtures thereof. With reference to the above formula, the sugars are acylated at

- 26 -


primary hydroxyl positions. For example, sucrose is acylated at the 1'- position, raffinose at the 1"- position, fructose at the 1- position, trehalose at the 6- position, α - and β - alkylglucosides at the 6- position, α - and β - haloglucosides at the 6- position, α - and β - alkylgalactosides at the 6- position, α - and β - halogalactosides at the 6- position, α - or β - alkylmannosides at the 6- position, and α - and β - halomannosides at the 6- position.

The acylated sugars are then polymerized by dissolving the sugars in either water or a non-aqueous organic solvent such as dimethylformamide, N-methylpyrrolidone, dimethylsulfoxide or dimethyl acetamide (dimethylformamide being preferred) and thereafter sparging the resulting mixture with nitrogen for about ten minutes at about 40°C. Other methods of agitation may, of course, be used in place of sparging with nitrogen. Thereafter, a free radical initiator is added to the solution in an amount from about .05% to about 0.5% by weight initiator per weight acylated sugar monomers. The molecular weight of the final product is inversely proportional to the amount of initiator added.

Where water is the solvent, an equal amount of potassium persulfate and hydrogen peroxide initiators are preferably added. Where a substantially non-aqueous organic solvent is used, preferred initiators include azobisisobutyrol-nitrile, benzoyl peroxide and tert-butyl peroxide. In either case, the resulting mixture is mixed (250 rpm) at about 40°C for about 24 hours. The resulting sugar-based polymer can then be recovered by precipitation with acetone, filtered and dried.

The resulting sugar-based polymer will have the general formula:

- 27 -



wherein S comprises non-reducing sugar, R is selected from the group consisting of hydrogen, alkanes, alkenes, branched alkanes, substituted alkenes, aromatic moieties, substituted aliphatic moieties, substituted aromatic moieties and mixtures thereof, and n is a number greater than 1. With reference to the above formula, the sugars are attached at primary hydroxyl positions. For example, sucrose is attached at the 1'-position, raffinose at the 1"-position, fructose at the 1'-position, trehalose at the 6-position, alkyl-and haloglucosides at the 6-position, alkyl-and halogalactosides at the 6-position and alkyl-and halomannosides at the 6-position.

CROSS-LINKING OF THE SUGAR-BASED POLYMERS

In some applications it may be desirable to cross-link the sugar-based polymers of the present invention. For example, where shorter linking groups (i.e. for example the R₂ group in the previously discussed organic acid derivative) are employed (i.e. less than about 10 carbons), the polymer will be hydrophilic and potentially water soluble. Light cross-linking would result in an insoluble hydrophilic polymer that could swell and absorb water. This will be particularly important with lower molecular weight polymers. One approach of providing cross-linking capability to the sugar-based polymer is via the incorporation of an unsaturated fatty acid into the sugar-based polymer. This could be accomplished, for

- 28 -

example, by the use of an unsaturated fatty acid in the organic diacid derivative or in the coreactant. This would result in the incorporation of unsaturated fatty acid chains in the sugar-based polymer. Heating or irradiating the polymer would cause cross-linking to occur at the unsaturated bonds resulting in a thermo-setting or photostetting sugar-based polymer.


Another approach is to cross-link open hydroxyl positions on the sugars using a cross-linking species such as a diisocyanate or dinitrile. Preferred cross-linking species include 1,4-tetramethylene diisocyanate, 1,6-hexamethylene diisocyanate and 1,6-hexamethylene dinitrile in the presence of a trialkylamine catalyst (with respect to the use of a dinitrile cross-linking agent, the cross-linking is acid catalyzed rather than trialkyl amine catalyzed). For all practical purpose, however, only a limited amount of cross-linking is suggested pursuant to this method. Generally, no more than one hydroxyl per sugar moiety should be cross-linked. Excessive cross-linking may result in the removal of too many free hydroxyl groups, thereby reducing the water-absorbency of the sugar-based polymer. The polymers could also be cross-linked during the acylation process by using organic acid derivatives having three or four carboxyl groups, the free carboxyl groups acting as cross-linking points. Of course, any method of cross-linking known by those skilled in the art is contemplated for use in the present invention.

PREPARATION OF SUGAR-CONTAINING POLY(ACRYLATE)-BASED HYDROGELS

Surprisingly, it has been discovered that water-absorbant hydrogels may be prepared using the poly(sugar acrylates) of the present invention. Preferably, monosaccharide-based poly(acrylates) are used to prepare the hydrogels of the present invention.

- 29 -

In particular, the previously discussed acylated sugars, of which the acylated monosaccharides are preferred, used in the preparation of poly(sugar acrylates) are employed in preparing the hydrogels. Thus, acylated sugars are provided having the following structure:



wherein S comprises sugar, R is selected from the group consisting of hydrogen, straight chain alkanes having from about 1-10 carbon atoms, phenyl, nitrophenyl and mixtures thereof. Preferably, R is a hydrogen atom.

The sugar is preferably selected from the group consisting of sucrose acylated at the 1'-position, raffinose at the 1"-position, fructose at the 1-position, trehalose at the 6-position, α - and β -phenyl- or alkylglucosides at the 6 position, α - and β -haloglucosides at the 6-position, α - and β -phenyl- or alkylgalactosides at the 6-position, α - and β -halogalactosides at the 6-position, α - or β -phenyl- or alkylmannosides at the 6-position, α - and β -halomannosides at the 6-position, and mixtures thereof. More preferably the sugar is selected from the acylated monosaccharides of the foregoing group. Even more preferably, the sugar is selected from the methylated monosacharrides of the foregoing group. Most preferably, the sugar comprises 1-methylgalactoside.

In preparing the hydrogels of the present invention, the acylated sugar is polymerized by mixing the acylated sugar with a free-radical polymerization initiator. Any suitable free-radical initiator is contemplated for use in the present invention. Examples of suitable initiators ammonium persulfate in water, t-butyl peroxide or azobisisobutyrol-nitrile (AIBN) in non-aqueous solvents. Preferably, the initiator will comprise AIBN.

- 30 -

In an alternate embodiment of the present invention, the acylated sugar is copolymerized with an equimolar amount of 2-hydroxyethyl methacrylate.

5 The free radical polymerization, or the copolymerization as the case may be, is conducted in the presence of a crosslinking agent. Any suitable crosslinking agent is contemplated for use in the present invention. Thus, any compound having two terminally located vinyl groups is contemplated for use
10 in the present invention. Preferably, the crosslinking agent comprises ethyleneglycol dimethacrylate. Preferably, the crosslinking agent will comprise about 0.1 - 10% by weight of the polymer or copolymer. Even more preferably, it will comprise 0.3-3 wt% of the
15 polymer.

In the presently most preferred embodiment of the invention, the hydrogel is made without the presence of a free-radical polymerization initiator or a cross-linking agent. In this embodiment, a sugar-
20 based homopolymer is made from an acylated sugar as previously disclosed and as disclosed in the examples set forth herein. The resulting acylated sugar is purified in a silica gel column as disclosed herein (See, for example, Example 12). The resulting
25 composition comprises acylated sugar, ethyl acetate and traces of water. The ethyl acetate and water are evaporated off by rotary evaporation at about 60°C to concentrate the acylated sugar. As the acylated sugar concentrates during the rotary evaporation (until the
30 concentrated acylated sugars have an oil-like viscosity), it autopolymerizes to give the hydrogels of the present invention.

It is to be understood that an equivalent of changes and modification of the above described embodi-
35 ments are also contemplated for use in the present invention. The following examples are not to be construed as limitations upon the present invention,

- 31 -

the scope of which is defined by the claims appended hereto, but are included merely as an illustration of various embodiments.

5

EXAMPLES

Example 1

10

15

20

25

30

In order to identify enzymes capable of catalyzing the regioselective diacylation of sucrose and, ultimately, the synthesis of sucrose-based polymers, a variety of hydrolytic enzymes were screened for their ability to synthesize sucrose butyrate in pyridine. In this manner, simple esters of sucrose were obtained and structurally analyzed without the added complication of polymer formation. Trifluoroethylbutyrate was chosen as the butyrate donor. In all, 15 enzymes were studied for sucrose-butyrate synthesis (Table 1). A typical reaction mixture contained 0.1 M sucrose dissolved in 2 mL anhydrous pyridine containing 0.6 M trifluoroethylbutyrate. The 6:1 molar ratio of trifluoroethylbutyrate to sucrose was chosen to expedite the reaction. The reactions were initiated by the addition of 0.25 g/mL enzyme (0.015 g/mL in the case of "proleather", an alkaline protease obtained from Amano) and mixing at 250 rpm and 45°C. Sucrose disappearance was monitored by HPLC. As can be discerned from Table 1, the five most active enzymes were Alkaline Protease; Bacterial Protease; Bacillus protease; Aminoacylase; and subtilisin.

Example 2

35

The five most catalytically active enzymes from Example 1 were subjected to a 25 mL reaction scale (same concentrations of reactants and enzyme as in Example 1). After the time scale indicated in Table 2 the reactions were terminated and the solvent evaporated. The residual solids were chromatographed

- 32 -

on silica gel (17:2:1; ethyl acetate:methanol:water) and the sucrose ester products separated. Clearly, as can be discerned from Table 2, the alkaline protease ("proleather") produced the highest ratio of sucrose dibutyrate to monobutyrate. The production of the sucrose dibutyrate is important for the subsequent synthesis of the sucrose-based polymer of the present invention. ¹³C-NMR analysis of the proleather mono- and diester products indicated that the sucrose is first acylated in the 1' position followed by acylation at the 6 position.

Example 3

As can be discerned from TABLES 1 and 2, of the fifteen enzymes considered, proleather was the ideal choice to carry out the synthesis of a sucrose-based polymer. In this example, bis(2,2,2-trifluoroethyl) adipate was selected as the organic acid derivative. Sucrose (0.1 M) was dissolved in 25 mL anhydrous pyridine containing 0.1 M bis(2,2,2-trifluoroethyl) adipate. The reaction was initiated by the addition of 0.015 g/mL activated alkaline protease (proleather) and the reaction magnetically stirred at 100 rpm and 45°C under a slight nitrogen stream. The ratio of sucrose to the diacid derivative was purposely chosen to be equimolar as it was expected that two hydroxyls on sucrose would readily react with the two acid functionalities of the organic acid derivative. (Proleather did not catalyze the synthesis of sucrose tributyrates in the aforementioned experiment.)

The progress of the reaction was followed by gel permeation chromatography (gpc) HPLC. The reaction was terminated after 28 days (80% conversion of the sucrose), the enzyme removed by filtration, and the pyridine and bis(2,2,2-trifluoroethyl) adipate removed by rotary evaporation. The products of the reaction were completely water-soluble as well as having high

- 33 -

solubilities in polar organic solvents including methanol, ethanol, pyridine, dimethylformamide, and dimethylsulfoxide. While the reaction was slow, gpc data showed the formation of higher molecular weight species as reaction time increased. Molecules with molecular weights in excess of 10,000 were produced. The average molecular weight was determined following dialysis of the product (through a 1000 dalton dialysis bag to remove unreacted sucrose and low molecular weight mono- and diester products). The dialyzed product was shown to have a weight average molecular weight (M_w) of 2110 and a number average molecular weight (M_n) of 1555, therefore giving a polydispersity (M_w/M_n) of 1.36. The polyester showed selective linkages between the adipic acid functionalities and the 6 and 1' positions of the sucrose as determined by ^{13}C -NMR. From the NMR data, it is clear that a shift in the positions of the 6 and 1' carbons has occurred, indicative of acylation at those positions. The resulting sucrose-based polymer had a decomposition temperature of about 150°C.

Example 4

A sugar-based polymer comprising poly(raffinose adipate) was prepared according to the following steps. An equimolar amount of raffinose and bis(2,2,2-trifluoroethyl) adipate were mixed in the presence of 375 mg proleather in 25 mL pyridine. The resulting mixture was mixed at 250 rpm for ten days resulting in the formation of a poly(raffinose adipate) having a $M_w = 13,000$, a $M_n = 11,000$ thereby yielding a polydispersity (M_w/M_n) of 1.18.

Example 5

A sugar-based polymer was prepared as in Example 4 except vinyl adipate was used instead of bis(2,2,2-trifluoroethyl)adipate.

- 34 -

Example 6

The chemoenzymatic synthesis of a poly(sucrose adipamide) was carried out using the following procedure. A reaction mixture was prepared by dissolving 0.86g (0.1M) sucrose in 25 mL pyridine containing 3.1g (0.4M) bis (2,2,2-trifluoroethyl-adipate). Excess bis (2,2,2-trifluoroethyladipate) was used to improve the yield of sucrose diester relative to the monoester. The diacylation of sucrose was initiated by the addition of 15 mg/mL Proleather (an activated alkaline protease from a Bacillus sp.) to the reaction mixture and subsequent magnetic stirring of the mixture under nitrogen at 150 rpm for 5 days at 45°C. The diacylation of the sucrose was terminated by filtering off the enzyme and evaporating the pyridine and unreacted bis(2,2,2-trifluoroethyladipate). The resulting sucrose 6,1'-di(trifluoroethyl)adipate was then purified using silica gel chromatography with an eluent of ethyl acetate: methanol: water (18:1.25:1). The sucrose 6,1'-di(trifluoroethyl)adipate was obtained in 20% yield. No triester was formed.

Polymerization of the 6,1'-di(trifluoroethyl)adipate was then carried out by mixing 15 mg (0.125M) ethylenediamine and 0.19g (0.125M) 6,1'-di(trifluoroethyl)adipate in 2 ml of N-methylpyrrolidone. This solution was stirred at 35°C for 24 hours. Results of gel permeation (GPC) and thin layer (TLC) chromatographies indicated that the conversion of the 6, 1' di(trifluoroethyl)adipate was quantitative. A substantial byproduct (ca. 50%) was found to be sucrose mono adipate, presumably formed by the reaction of ethylenediamine with the internal ester linkage between the sucrose and the adipate derivative. The resulting poly(sucrose adipamide) was recovered by evaporating the N-methylpyrrolidone under vacuum at 50°C. The product was washed with acetone and dried under vacuum at 45°C. The poly(sucrose adipamide) was

- 35 -

obtained in 48% recovered yield (75 mg) and was a semicrystalline solid, having a melting point of 225°C; $[\alpha]_{D=16}^{25}$ (cl, dimethylformamide), $M_n=4800$, $M_w=8100$; Anal. calcd. for $C_{26}H_{42}O_{15}N_2$ (per repeat unit): C, 50.2; H, 6.8; O, 38.6; N, 4.5; found C, 48.9; H, 6.8; O, 33.1; N, 6.6. The slight decrease in ratio of O/N may have been due to the formation of trace amounts of poly(ethylene adipamide). The poly(sucrose adipamide) was insoluble in water, but soluble in a variety of polar organic solvents including pyridine, dimethylformamide, N-methylpyrrolidone, dimethylsulfoxide, dimethylacetamide, methanol and ethanol. Structural analysis of the poly(sucrose adipamide) by infrared spectroscopy was consistent with incorporation of sucrose into the polymer backbone. NMR analysis indicate that the sucrose is linked at the 6 and 1' positions.

Example 7

A sugar-based polymer comprising poly(sucrose adipate) was chemically prepared according to the following steps. 855 mg of sucrose was acylated in the 6 and 1' position with a blocking compound by mixing the sucrose and 1.3 g of the blocking compound consisting of vinyl acetate in the presence of 375 mg proleather in pyridine. The resulting diacylated sucrose was then mixed with an excess of methyl iodide (0.7 g) in the presence of 2 g dimethylaminopyridine. The resulting methylated sucrose was then mixed with an excess sodium hydroxide to deacylate (deblock) the primary hydroxyl groups at the 6 and 1' sites. Thereafter, the methylated sucrose having free primary hydroxyl groups at the 6 and 1' positions was polymerized by mixing it with 455 mg adipoyl chloride in the presence of 25 ml dimethylformamide. The mixture was treated with excess of acid to deblock the hydroxyl groups and the resulting poly(sucrose adipate)

- 36 -

was separated. The resulting polymer had a M_w of about 4,000.

Example 8

5 A water absorbent sugar-based polymer comprising poly(sucrose adipate) was made by cross-linking OH (secondary hydroxyl) groups on the sucrose moieties. In particular, 50 mg poly(sucrose adipate), 37.5 mg 1,6-hexamethylene diisocyanate and 10 mg of
10 triethylamine (catalyst) were mixed in 1 ml of dimethylformamide. This composition was mixed at 250 rpm (orbital mixer) for about 48 hours at ambient temperature (about 25°C) or until gel formation signifying cross-linking. The cross-linked
15 poly(sucrose adipate) made by this method was found to absorb 111% of its weight in H_2O . The absorbency of the polymer product was measured by adding 25 mg of the polysucrose adipate to water with gentle stirring for about 5 hours. The water was then removed by filtering
20 and the poly(sucrose adipate) was again weighed. The polymers' final weight/original weight (25 mg) provides the measure of its water absorbency.


Example 9

25 A water absorbent sugar-based polymer comprising poly(raffinose adipate) was made by cross-linking -OH groups on the raffinose moieties. In particular, 55 mg of poly (raffinose adipate), 37.5 mg 1,6-hexamethylene diisocyanate and 10 mg triethylamine
30 were mixed in 1 ml of dimethylformamide. This composition was mixed at 250 rpm for about 48 hours at ambient temperature or until a white solid formed. The cross-linked poly(raffinose adipate) made by this method was found to absorb 426% of its weight in water.
35 Absorbency was measured as in Example 8.

- 37 -

Example 10

A poly(sucrose adipate) is made by dissolving alkylated sucrose in dimethyl formamide. To this solution, a catalytic amount of dimethylaminopyridine and equimolar ratio of adipoyl chloride to sugar is added. The resulting mixture is mixed at 250 rpm for about 1 hour at 25°C. The resulting poly (sucrose adipate) has the structure



wherein S is sucrose linked at the 6 and 1' positions and n is greater than 100.



Example 11

A poly (sucrose acrylate) was made by dissolving 3.42 g (0.1 M) sucrose in 100 ml pyridine containing 5.88 g (0.6 M) vinyl acrylate. Hydroquinone (0.5% w/v) was added inhibit polymerization of the vinyl acrylate during the sucrose acrylate synthesis. The sucrose acrylate synthesis was initiated by addition of 15 mg/ml Proleather and the mixture was magnetically stirred under nitrogen at 150 rpm for 5 days at 45°C. The reaction was terminated by filtering of the enzyme, evaporating the pyridene and unreacted vinyl acrylate, and the product was purified and separated by silica gel chromatography with an eluent consisting of ethyl acetate:methanol:water (18:1.25:1). The sucrose monoester was obtained in 28% yield, 1.10 g. The ester was an amorphous solid, mp = 78°C; $[\alpha]_D^{25} = 50.4$ (c1, H₂O).

Subsequent poly(sucrose acrylate) synthesis was carried out by dissolving 0.1 g (0.25 M) of the sucrose monoester in 1 ml H₂O and the solution was sparged with N₂ for ten minutes. Potassium persulfate

- 38 -

(0.15%) and 0.2% hydrogen peroxide were added and the solution was stirred at 25°C for 24 hours. The resulting poly (sucrose 1'-acrylate) was recovered by precipitation with acetone, filtered and dried under vacuum at 45°C. The poly (sucrose 1'-acrylate) was obtained in 80% yield (80 mg), and was characterized as an amorphous solid, $[\alpha]_D^{25} = 38.3$ (0.67, H₂O), $M_n = 57,000$, $M_w = 91,000$. Anal. calcd. for C₁₅H₂₃O₁₂ (per repeat unit); C, 45.5; H, 6.1; O, 48.5; found C, 43.2; H, 5.9; O, 47.0. The poly (sucrose 1'-acrylate) was soluble in a variety of polar organic solvents including water, dimethylformamide, and N-methylpyrrolidone. As confirmed by IR analysis, the poly (sucrose 1'-acrylate) had the following structure:



Sucrose

Example 12

Enzymatic Synthesis of 1-β-Methyl-6-Acryloyl-Galactoside

A solution of 3.0 g (0.4 M) 1-β-D-methylgalactoside in 40 mL anhydrous pyridine was prepared and 3.3 mL (0.6 M) vinyl acrylate was added. The reaction was initiated by the addition of 0.25 g/mL lipase P and the mixture stirred at 200 rpm at 25°C. After 40h, 97% of the substrate had reacted. The reaction was stopped by filtering off the enzyme and the filtrate was dried under rotary vacuum to give a tan oil. The oil was subjected to silica gel chromatography (4 x 60 cm) with ethyl acetate:MeOH:H₂O (720:5:4). The fractions corresponding to 1-β-methyl-6-acryloyl-galactoside were pooled and dried to give

- 39 -

2.92 g (75% yield) of a white powder. $[\alpha]_D^{25}$ - 10.1 (c 1, DMF). ^1H NMR (DMSO- d_6) δ 3.53 (dd, $J=9.91$, 7.90 Hz, H-2), 3.56 (3H, s, $\text{CH}_3\text{O}-$), 3.67 (1H, dd, $J=9.91$, 3.52 Hz, H-3), 3.97 (1H, m, H-5), 3.99 (1H, d, $J=3.52$ Hz, H-4), 4.34 (1H, d, $J=7.90$ Hz, H-1), 4.38 (1H, dd, $J=11.7$, 4.8 Hz, H-6), 4.40 (1H, dd, $J=11.7$, 7.7 Hz, H-6), 6.03 (1H, dd, $J=10.58$, 0.92 Hz, H-3'), 6.24 (1H, dd, $J=10.58$, 17.37 Hz, H-2'), 6.47 (1H, dd, $J=17.37$, 0.92 Hz, H-3'). ^{13}C NMR δ : 59.97 (CH_3O), 66.49 (C-6), 71.41 (C-4), 73.34 (C-2), 75.23 (C-5), 75.39 (C-3), 106.6 (C-1), 129.9 (C-2'), 136.2 (C-3') and 170.9 (C=O). Anal. Calcd. for $\text{C}_{10}\text{H}_{16}\text{O}_7$: C, 48.39; H, 6.69; O, 45.16. Found: C, 48.38; H, 6.45; O, 45.29.

Example 13

Enzymatic Synthesis of 1- β -Phenyl-6-Acryloyl-Galactoside

A solution of 4.08 g (0.4 M) 1- β -D-phenylgalactoside in 40 mL anhydrous pyridine was prepared and 3.3 mL (0.6 M) vinyl acrylate was added. The reaction was initiated by the addition of 0.25 g/mL lipase P and the mixture stirred at 200 rpm at 25°C. After 40 h, 98% of the substrate had reacted. The reaction was stopped by filtering off the enzyme and the filtrate was dried under rotary vacuum to give a tan oil. The oil was subjected to silica gel chromatography (4 x 60 cm) with ethyl acetate:MeOH:H₂O (720:2:1). The fractions corresponding to 1- β -phenyl-6-acryloyl-galactoside were pooled and dried to give 2.95 g (59% yield) of a white powder. $[\alpha]_D^{25}$ -24.3 (c 1, DMF). ^1H NMR (DMSO- d_6) δ 3.52 (1H, dd, $J=9.45$, 3.34 Hz, H-3), 3.64 (1H, dd, $J=9.45$, 7.77 Hz, H-2), 3.78 (1H, br d, $J=3.34$ Hz, H-4), 3.96 (1H, ddd, $J=8.37$, 3.94, 0.86 Hz, H-4), 4.25 (1H, dd, $J=11.43$, 3.94 Hz, H-6), 4.38 (1H, dd, $J=11.43$, 8.37 Hz, H-6), 4.88 (1H, d, $J=7.77$ Hz, H-1), 6.03 (1H, dd, $J=10.41$, 1.48 Hz, H-3'), 6.23 (1H, dd, $J=17.37$, 10.41 Hz, H-2'), 6.39 (1H, dd,

- 40 -

$J=17.37$, 1.48 Hz, H-3'), 7.04 (3H, m, H-3", -4", -5"), 7.31 (1H, ddd, $J=7.35$, 2.35 , 2.07 Hz, H-2" or H-6"), 7.32 (1H, ddd, $J=7.31$, 2.32 , 2.04 Hz, H-2" or H-6"). ^{13}C NMR δ 65.44 (C-6), 69.83 (C-4), 71.61 (C-2), 73.97 (C-5), 74.55 (C-3), 102.2 (C-1), 117.7 (C-3", -5"), 123.2 (C-4"), 129.7 (C-2'), 130.8 (C-2",), 133.1 (C-3'), 158.9 (C-1"), 166.7 (C=O). Anal. Calcd. for $\text{C}_{15}\text{H}_{18}\text{O}_7$: C, 58.06; H, 5.81; O, 36.13. Found: C, 57.87; H, 6.01; O, 35.90.

Example 14

Enzymatic Synthesis of 1- β -(2-NO₂-Phenyl)-6-Acryloyl-Galactoside

A solution of 4.82 g (0.4 M) 1- β -D-2-nitrophenylgalactoside in 40 mL anhydrous pyridine was prepared and 3.3 mL (0.6 M) vinyl acrylate was added. The reaction was initiated by the addition of 0.25 g/mL lipase P and the mixture stirred at 200 rpm at 25°C . After 20 h, 95% of the substrate had reacted. The reaction was stopped by filtering off the enzyme and the filtrate was dried under rotary vacuum to give a tan oil. The oil was subjected to silica gel chromatography (4×60 cm) with ethyl acetate:MeOH:H₂O ($720:2:1$). The fractions corresponding to 1- β -(2-nitro-phenyl)-6-acryloyl-galactoside were pooled and dried to give 4.56 g (80% yield) of a white powder. $[\alpha]_D^{25} -96.9$ (c 1 , DMF). ^1H NMR (DMSO- d_6) δ 3.47 (1H, br d, $J=9.2$ Hz, H-3), 3.60 (1H, m, H-2), 3.74 (1H, t, $J=3.68$, H-4), 4.01 (1H, m, H-5), 4.22 (1H, dd, $J=4.02$, 11.47 , H-6), 4.28 (1H, dd, $J=8.29$, 11.47 Hz, H-6), 5.08 (1H, d, $J=8.72$ Hz, H-1), 5.98 (1H, dd, $J=10.40$, 1.46 Hz, H-3'), 6.18 (1H, $J=17.29$, 10.40 Hz, H-2'), 6.38 (1H, $J=17.29$, 1.46 Hz, H'3'), 7.18 (1H, dt, $J=8.2$, 0.86 , H'4"), 7.37 (1H, dd, $J=8.57$, 0.86 , H-6"), 7.60 (1H, dt, $J=8.5$, 1.7 Hz, H-5"), 7.85 (1H, dd, $J=8.07$, 1.7 Hz, H-3"). ^{13}C NMR δ 65.43 (C-6), 69.99 (C-4), 71.54 (C-2), 74.48 (C-5), 74.75 (C-3), 102.4 (C-1),

- 41 -

118.7 (C-6"), 123.5 (C-4"), 126.4 (C-3"), 129.9 (C-2'),
133.4 (C-3'), 135.5 (C-5"), 142.0 (C-2"), 151.1 (C-1"),
166.9 (C=O). Anal. Calcd. for $C_{15}H_{17}NO_9$: C, 50.70; H,
4.79; N, 3.94; O, 40.56. Found: C, 50.66; H, 5.20; N,
3.79; O, 40.20.

Example 15

Synthesis of Poly(1- β -Methyl-6-Acryloyl-Galactoside)

A solution of 2.0 g 1- β -methyl-6-acryloyl-galactoside in 8mL DMF was prepared and 0.1% (w/w) AIBN was added. The polymerization proceeded at 65° under nitrogen for 16 h. The reaction was terminated by precipitating the polymer with ethyl acetate and the white solids were washed with acetone to yield 1.48 g poly(1- β -methyl-6-acryloyl-galactoside) (74% yield). $[\alpha]_D^{25}$ - 12.8 (c 1, DMF). 1H NMR (DMSO- d_6) δ 1.80 (2nH, br t, H-3'), 2.44 (1nH, br s, H-2'), 3.55 (1nH br s, H-2), 3.60 (3nH, s, CH_3O), 3.70 (1nH, br s, H-3), 3.90 (1nH, br s, H-5), 3.97 (1nH, br s, H-4), 4.27 (2nH, br s, H-6) and 4.32 (1nH, br s, H-1). ^{13}C NMR δ 21.08 (C-3'), 44.23 (C-2'), 59.60 (CH_3O), 67.26 (C-6), 71.49 (C-4), 73.29 (C-2), 75.19 (C-5), 75.44 (C-3), 106.5 (C-1), 167.6 (C=O). Anal. Calcd. for $C_{10}H_{16}O_7$: C, 48.39; H, 6.69; O, 45.16. Found: C, 48.27; H, 6.86; O, 45.38.

Example 16

Synthesis of Poly(1- β -Phenyl-6-Acryloyl-Galactoside)

The polymerization reaction was performed under conditions identical to the previous example regarding poly (1- β -methyl-6-acryloyl-galactoside). The polymerization yielded 1.80 g of a white powder (90% isolated yield). $[\alpha]_D^{25}$ - 45.8 (c 1, DMF). 1H NMR (DMSO- d_6) δ 1.48 (1nH, br t, H-3'), 2.17 (1nH, br s, H-2'), 3.40 (1nH, br s, H-3), 3.75 (1nH br s, H-4), 4.00 (1nH, br s, H-5), 4.72, 4.90 (each 1nH, each br s, H-6), 5.20 (1nH, br s, H-1), 6.85 (3H, br s, H-3"-, 4"-, 5"), 7.10 (2H, br s, H-2"-, 6"). ^{13}C NMR δ 64.0 (C-6),

- 42 -

68.3 (C-4), 69.9 (C-2), 72.0 (C-5), 72.8 (C-3), 100.5 (C-1), 116.0 (C-3", -5"), 121.6 (C-4"), 129.2 (C-'2", -6"), 157.1 (C-1"), 162.2 (C=O). The carbon assignments for C-2' and C-3' were split into numerous signals due to mixtures of rotational configurations. Anal. Calcd. for $C_{15}H_{18}O_7$: C, 58.06; H, 5.81; O, 36.13. Found: C, 57.81; H, 6.04; O, 35.94.

Example 17

Synthesis of Poly(1- β -(2-NO₂-Phenyl)-6-Acryloyl-Galactoside)

The polymerization reaction was performed under conditions identical to Example 15 regarding poly(1- β -methyl-6-acryloyl-galactoside). The polymerization yielded 1.32 g of a white powder (66% isolated yield). $[\alpha]_D^{25}$ - 108.7 (c 1, DMF). ¹H NMR (DMSO-d₆) δ 1.50 (2nH, br t, H-3'), 2.21 (1nH, br s, H-2'), 3.51 (1nH, br s, H-3), 3.61 (1nH, br s, H-2), 3.75 (1nH, br s, H-4), 4.05 (1nH, br s, H-5), 4.78, 5.20 (each 1nH, each br s, H-6), 5.04 (1nH, br, s, H-1), 7.05 (1nH, br s, H-4"), 7.30 (1nH, br s, H-6"), 7.50 (1nH, br s, H-5"), 7.70 (1nH, br s, H-3"). ¹³C NMR δ 63.55 (C-6), 68.10 (C-4), 69.66 (C-2), 72.59 (C-5), 72.75 (C-3), 100.5 (C-1), 116.8 (C-6"), 121.7 (C-4"), 124.5 (C-3"), 133.7 (C-5"), 139.8 (C-2"), 149.2 (C-1"), 165.1 (C=O). The carbon assignments for C-2' and C-3' were split into numerous signals due to mixtures of rotational configurations. Anal. Calcd. for $C_{15}H_{17}NO_9$: C, 50.70; H, 4.79; N, 3.94; O, 40.56. Found: C, 50.25; H, 4.89; N, 4.28; O, 40.68.

Example 18

Synthesis of Hydrogels

The polymerization of 1- β -methyl-6-acryloyl-galactoside or 1- β -phenyl-6-acryloyl-galactoside were carried out in an identical fashion: 1.0 g of the monosaccharide acrylate was dissolved in 4.0 mL DMF

- 43 -

containing different concentrations of ethyleneglycol dimethacrylate (ranging from 0.5 to 6%, w/w) and 0.5% (w/w) AIBN was added. The reaction was performed at 60° C for 12 h during which time a gel formed. The residual DMF contained no traces of monosaccharide acrylate (as determined by TLC). Vacuum drying of the gels for 24 h (40°C) resulted in white solids with an average mass of 0.88 g. Water-swelling was measured by placing the solids in 25 mL water for 12 h followed by removal of the bulk liquid by filtration until surface dry gel was obtained and the material weighed. Poly (1- β -methyl-6-acryloyl-galactoside-hema) copolymers were prepared in a similar manner with the ethyleneglycol dimethacrylate concentration reduced to 0.3% (w/w).

Example 19

Synthesis of Poly(1- β -Methyl-6-Acryloyl-Galactoside)

The synthesis involved the preparation of 1- β -methyl-6-acryloyl-galactoside via enzyme-catalyzed transesterification of 1- β -D-methylgalactoside with vinyl acrylate in anhydrous pyridine. Several lipases were screened for their abilities to catalyze this reaction and the lipase from *Pseudomonas cepacia* (lipase P) was found to give the highest conversion of 1- β -D-methyl-galactoside to acrylate ester. Preparative acryloylation of 1- β -D-methylgalactoside resulted in the synthesis of 1- β -methyl-6-acryloyl-galactoside in 92% yield in 40 h with an additional (<5% by TLC) amount of a presumed diacrylate ester which was not further characterized. The reaction was terminated by filtering off the enzyme and the pyridine was evaporated to give a tan oil. The oil was subjected to a silica gel chromatography and 2.92 g 1- β -methyl-6-acryloyl galactoside was obtained (75% isolated yield) as a white powder. The structure was verified by ¹H- and ¹³C-NMR, and elemental analysis.

- 44 -

Polymerization of 2.0 g of the 1- β -methyl-6-acryloyl-galactoside was performed in DMF containing 0.1% AIBN. Following 24 h incubation, the reaction was terminated by precipitating the polymer with ethyl acetate and washing with acetone resulting in 1.48 g poly(1- β -methyl-6-acryloyl-galactoside) (74% isolated yield, and 56% overall isolated yield from 1- β -D-methylgalactoside). GPC analysis indicated an $M_w=135,000$ and $M_n=58,000$ ($M_w/M_n = 2.3$). The polymer was soluble in water and highly polar organic solvents including pyridine, DMF, and DMSO, and was highly hygroscopic. When 10 mg of powder was exposed to air for 30 min it absorbed 8 mg water from the atmosphere. Comparison of the ^{13}C -NMR spectra of 1- β -methyl-6-acryloyl-galactoside to the poly(1- β -methyl-6-acryloyl-galactoside) shows that the acrylate double bond in the former is absent in the latter.

Example 20

Monosaccharide Specificity of Pseudomonas Lipase

A variety of other monosaccharides were acryloylated by lipase P catalysis. Table III details the initial rates of acryloylation of these sugars in pyridine. The activity of lipase P was highly dependent on substrate structure. The enzyme clearly prefers galactosides over glucosides. For example, 1-methylgalactoside is 6 and 13-fold more reactive than methylglucoside for the α and β anomers, respectively. This difference may be due to the proximity of the C-4 hydroxyl moiety on acylation at the C-6 hydroxyl group. The poor reactivity of 1- α -D-methylmannoside (over 14-fold less reactive than 1- α -methyl-6-acryloyl-glucoside) however, is intriguing as mannose is the C-2 epimer of glucose (axial C-2 hydroxyl in mannose) which is remote from the C-6 position of acylation. To ascertain whether the axial hydroxyl at C-2 of mannose sterically did indeed hinder the binding of the sugar

- 45 -

into the lipase's active site, we acryloylated β -D-2-deoxyglucose (same as 2-deoxymannose) under equivalent conditions for 1- β -methyl-6-acryloyl-galactoside and compared the rate of acylation to that for free β -D-glucose. The rates of acylation were identical for these compounds (0.1 μ mol/mg powder-h; ca. 75% of that for 1- β -methyl-6-acryloyl-glucoside) indicating that the axial hydroxyl of mannose derivatives interferes with acylation, perhaps because of steric hinderance of the C-2 hydroxyl group. The binding of sugars to lipases must be similar to the binding of glycerol esters with the sugar occupying the same active-site subsite as the glycerol moiety. Acylation at C-6 of a monosaccharide places the C-2 five carbons distant from the position of acylation. It may be speculated that the alcoholic subsite of lipases is not large enough to accommodate an axial functionality that far away from the active center for acylation. Similarly, a bulkier aglycon moiety at position C-1 would be expected to reduce catalytic activity. In fact, this is observed as the bulkier phenyl group, in general (compare 1- β -phenyl-6-acryloyl-galactoside to 1- β -methyl-6-acryloyl-galactoside and 1- β -phenyl-6-acryloyl-glucoside to 1- α -methyl-6-acryloyl-glucoside) lowers the enzyme's activity anywhere from 4 to 7-fold.

Example 21

Synthesis of Other Poly(sugar acrylate)s

The acryloylation of the 6 position leaves open the possibility to control the polymeric properties by varying the aglycon moiety on the 1 position. This was further investigated by using 1- β -D-phenylgalactoside as the starting material for chemoenzymatic poly(acrylate) synthesis. In a similar manner as that of 1- β -methyl-6-acryloyl-galactoside, 1.80g of 1- β -phenyl-6-acryloyl-galactoside (53% overall isolated yield from 1- β -D-phenylgalactoside) was

- 46 -

synthesized. Polymerization was performed with AIBN in DMF and the resulting polymer was precipitated with acetone and dried. The poly(1- β -phenyl-6-acryloyl-galactoside) was a white solid with $M_w=52,700$ and $M_n = 28,900$ ($M_w/M_n = 1.8$) and was isolated in 40% yield. The polymer was water-insoluble but soluble in pyridine, DMF, and DMSO, and was not hygroscopic, in stark contrast to poly(1- β -methyl-6-acryloyl-galactoside). Hence, the additional hydrophobicity of the aglycon moiety significantly reduced the hydrophilicity of the polymer. Likewise, poly (1- β -(2-NO₂-phenyl)-6-acryloyl-galactoside) was synthesized using AIBN in DMF, however, the product was produced in low molecular weight ($M_w<10,000$). The low molecular weight was possibly due to the free radical scavenging ability of the nitro group.

Example 22

Preparation of Galactose-Based Hydrogels

Hydrogels are often prepared by polymerizing a water-soluble (meth)acrylic acid-containing compound in the presence of a small amount of crosslinker. Sugars are highly hydrophilic, water-soluble, and have the potential to comprise the functional parts of hydrogel matrices. The synthetic strategy involved the polymerization of 1.0 g of 1- β -methyl-6-acryloyl-galactoside in DMF with 0.5% (w/w) AIBN plus different amounts of ethyleneglycol dimethacrylate as crosslinker. The polymerization reactions were carried out for 12 h after which the residual DMF was removed by washing the copious amounts of water. The gel-like materials were vacuumed dried to give, on average, 0.88 g of a white solid. The solids were placed in water and allowed to equilibrate for 12 h. The percentage of water contained in the hydrogel based on 1- β -methyl-6-acryloyl-galactoside is independent of the crosslinker content between 0.5 and 6% (w/w) and is ca. 90%. Thus,

- 47 -

the hydrogel holds 9-times its weight in water. Conversely, a similar set of experiments with 1- β -(2-nitro-phenyl)-6-acryloyl-galactoside showed markedly poorer hydrogel characteristics (< 30%, w/w) (Figure 1) suggesting that the more hydrophobic aglycon moiety repelled water when directly compared to the methyl moiety. The hydrogel based on 1- β -methyl-6-acryloyl-galactoside contains methylgalactoside units packed close together. We reasoned that this might cause sugar-sugar interactions that could reduce the hydrophilicity of the gel. To avoid this tight packing of the sugar moieties, copolymerization of 1- β -methyl-6-acryloyl-galactoside with 2-hydroxyethyl methacrylate (hema) was carried out in equimolar concentrations in the presence of ethyleneglycol dimethacrylate as crosslinker and further improvement was observed in the amount of water contained in the hydrogel matrices. In the presence of 0.5% (w/w) crosslinker, the percentage of water contained in the hydrogel reached 95% and reached 98% with 0.3% crosslinker. Attempts to reduce the crosslinker content below 0.3% failed to produce a gel material. Hence, the hydrogel based on 50% 1- β -methyl-6-acryloyl-galactoside and 50% hema holds up to 50-fold its weight in water. The lower the crosslinker concentration, the higher the water content of the resulting hydrogel. This is consistent with the less rigid nature of lightly crosslinked polymers. As a comparison, hema was polymerized in the absence of 1- β -methyl-6-acryloyl-galactoside with 0.3% (w/w) crosslinker. The poly(hema)-based hydrogel was capable of holding ca. 5-fold its weight in water. Thus, the presence of hydrophilic sugar moieties in the hydrogel improves the water-swelling characteristics of a hema-based crosslinked polymer.

- 48 -

In Examples 12-22:

Lipases P (from *Pseudomonas cepacia*), Ay (from *Candida rugosa*), and G (*Penicillium* sp.) were obtained from Amano Enzyme Co. (Philadelphia, PA). Porcine pancreatic lipase was obtained from Sigma (St. Louis, MO) and Lipolase was a gift from Novo Nordisk (Bagsvaerd, Denmark). All sugars were obtained from Sigma and the vinyl acrylate was purchased from Tokyo Kasei (Portland, OR). Azobisisobutyronitrile (AIBN), poly(ethylene glycol) molecular weight standards (200-20,000), dextrans (10,000 - 170,000) and polystyrenes (1,000 - 100,000) were obtained from Polysciences (Warrington, PA). All other compounds and solvents were of the highest purity commercially available. Pyridine was dried prior to use with Linde molecular sieves (4 Å) for 24 h. Optical rotations were measured at 589 nm (sodium line) at 25°C in a Jasco DIP-360 optical polarimeter. ¹H and ¹³C NMR were recorded on a Brüker WM 360 MHz instrument with TMS as internal reference and DMSO-d₆ used as the solvent in all cases.

Enzymatic reactions were followed by HPLC for the conversions of the sugar glycoside starting materials. A carbohydrate analysis column (Waters Assoc., Milford, MA) was used with an elution system consisting of 83% acetonitrile and 17% water. Detection was performed by refractive index (Model 410, Waters). Gel permeation chromatography (GPC) of Poly(1-β-methyl-6-acryloyl-galactoside) was performed using an Ultrahydrogel Linear column (Waters) with an eluant of 0.1 M NaNO₃ and a flow rate of 1 mL/min. Molecular weight calibration was performed with poly(ethylene glycol) and dextran standards. GPC of 3 poly(1-β-phenyl-6-acryloyl-galactoside) and 3 poly(1-β-(2-NO₂-phenyl)-6-acryloyl-galactoside) were performed with an Ultrastyrogel 10⁴ Å pore size (Waters) with DMF

- 49 -

as eluant (1 mL/min) and polystyrenes as molecular weight standards.

5 It is to be understood that a variety of sugars, organic acid derivatives, organic solvents, and hydrolytic enzymes can be substituted for those specified above and mixed in similar proportions to make various sugar-based polymers. The preceding examples should in no way be construed as limiting the extent of the present invention, the scope of which is
10 defined by the following claims.

- 50 -

TABLE 1

Screen of Enzymes for Sucrose-Butyrate Synthesis*

<u>Enzyme</u>	<u>Sucrose Conversion (120 h)</u>
Control (no enzyme)	0%
Lipase from <u>Aspergillus</u> Sp.	0%
Aminoacylase	70%
Lipozyme (Novo)	8%
Fungal Amylase (HT from Rohm)	34%
Bacterial protease (Bioenzyme)	100%
Amylase from <u>B. subtilis</u>	24%
(Rapidase from Gist-Brocades)	
<u>Rhizopus</u> Sp. Lipase	0%
Alkaline protease (Amano- Proleather)	96%
<u>Bacillus</u> protease	65%
Lipase from <u>Pseudomonas</u> Sp. (Amano P)	0%
Lipase from <u>C. cylindracea</u> (Sigma)	7%
Lipase from porcine pancreas (Sigma)	13%
Yeast Esterase (Sturge, Ltd.)	0%
Crude subtilisin (Amano protease N)	83%
Lipase from <u>Penicillium</u> Sp. (Amano G)	(in dimethylformamide) 24%

Conditions: Sucrose (0.1 M) dissolved in 2 Ml
pyridine containing 0.6 M trifluoroethylbutyrate.
Reaction initiated by addition of 0.25 g/ml enzyme and
shaken at 250 rpm at 45°C.

- 51 -

TABLE 2

Enzymatic Synthesis of Sucrose Butyrates^a

Total				
Enzyme	Conversion	Isolated Yield	1'-Ester	6,1'-Diester
Alkaline Protease (Proleather)	99% (8 days)	0.5 g (43%)	0.12 g	0.38 g
Bacterial Protease (Bioenzyme)	100% (8 days)	0.57 g (52%)	0.30 g	0.27 g
<u>Bacillus</u> Protease	62% (21 days)	0.39 g (37%)	0.31 g	0.08 g
Aminoacylase	67% (23 days)	0.54 g (49%)	0.26 g	0.28 g
Crude Subtilisin in Dimethylformamide	62% (25 days)	0.91 g (84%)	0.66 g	0.25 g

^aConditions: Sucrose (0.1 M) dissolved in 25 Ml pyridine (except with subtilisin) containing 0.25 g/Ml enzyme and 0.6 M trifluoroethylbutyrate, magnetically stirred at 150 rpm at 45°C.

- 52 -

TABLE 3

Initial Rates of Lipase P-Catalyzed Acryloylation
of Monosaccharide Glycosides in Pyridine^a

Compound	Initial Rate ^b ($\mu\text{mol}/\text{mg}$ powder-h)	Conversion ^c , %
1- β -methyl-6-acryloyl-galactoside	1.70	86
1- β -phenyl-6-acryloyl-galactoside	0.40	91
1- β -2-nitrophenyl-6-acryloyl-galactoside	0.45	93
1- β -methyl-6-acryloyl-glucoside	0.13	45
1- α -methyl-6-acryloyl-galactoside	0.82	74
1- α -methyl-6-acryloyl-glucoside	0.13	73
1- β -phenyl-6-acryloyl-glucoside	0.18	70
1- α -phenyl-6-acryloyl-glucoside	0.036	62
1- α -D-methylmannoside	0.009	39

^aConditions: 0.4 M Monosaccharide glycoside; 0.6 M vinyl acrylate; 2 mL pyridine containing 0.25 g/mL lipase P. The reactions were shaken at 250 rpm at 30°C.


^bMeasured via HPLC for the disappearance of monosaccharide glycoside.

^cAfter 30 h, except for 1- β -2-nitrophenyl-6-acryloyl-galactoside which was after 20h.

- 53 -

WE CLAIM:

1. A method of preparing a hydrogel comprising:
providing a concentrated solution comprising
acylated sugar having the structure:



wherein S is selected from the group consisting of sucrose acylated at the 1'-position, raffinose at the 1"- position, fructose at the 1- position, trehalose at the 6- position, α - and β -phenyl- or alkylglucosides at the 6-position, α - and β - haloglucosides at the 6-position, α - and β -phenyl- or alkylgalactosides at the 6- position, α - and β -halogalactosides at the 6-position, α - and β -phenyl-or alkylmannosides at the 6-position, α - and β - halomannosides at the 6-position, and mixtures thereof;

R is selected from the group consisting of hydrogen, straight chain alkanes having about 1-10 carbon atoms, and mixtures thereof; and

heating the composition to greater than about 60°C such that the acylated sugar autopolymerizes to form a hydrogel.

2. The method of claim 1 wherein S is selected from the group consisting of α - and β - methyl glucosides, α - and β -methyl galactosidies and mixtures thereof.


3. The method of claim 1 wherein S comprises β -methyl galactoside.

4. The product made by the method of claim 1.

5. The product made by the method of claim 2.

6. The product made by the method of claim 3.

7. A method of preparing a hydrogel comprising:
providing an amount of acylated sugar having
the structure:



wherein S is selected from the group consisting of sucrose acylated at the 1'-position, raffinose at the 1"-position, fructose at the 1-position, trehalose at the 6-position, α - and β - phenyl- or alkylglucosides at the 6-position, α - and β -haloglucosides at the 6-position, α - and β - phenyl- or alkylgalactosides at the 6-position, α - and β - halogalactosides at the 6-position, α - and β - phenyl- or alkylmannosides at the 6-position, α - and β - halomannosides at the 6-position and mixtures thereof;

R is selected from the group consisting of hydrogen, straight chain alkanes having from 1-10 carbon atoms, and mixtures thereof;

providing an amount of free-radical
polymerization initiator;

providing an amount of cross-linking agent;
and

mixing the acylated sugar, free radical
initiator and cross-linking agent to form a hydrogel.

8. The method of claim 7 wherein the free radical initiator comprises azobisisobutyrol-nitrile and the cross-linking agent comprises ethylene dimethacrylate.

9. The method of claim 8 wherein S comprises β methylgalactoside.

- 55 -

10. The method of claim 9 wherein about 0.5-6% ethylene glycol dimethacrylate by weight acylated sugar is provided.

11. The method of claim 10 further comprising the step of copolymerizing the acylated sugar with 2-hydroxyethyl methacrylate.

12. The product made by the method of claim 7.

13. The product made by the method of claim 8.

14. The product made by the method of claim 9.

15. The product made by the method of claim 10.

16. The product made by the method of claim 11.

INTERNATIONAL SEARCH REPORT

In national application No.
PCT/US93/12556

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : CO7H 1/00, 15/04

US CL : 536/116, 119, 120, 122, 124, 126

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 536/116, 119, 120, 122, 124, 126

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS, STN

search terms: methacryloyl(2w)glucose

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 3,225,012 (Black et al) 21 December 1965, Example 2.	1-16
Y	US, A, 3,400,107 (Black et al) 03 September 1968, Example 2.	1-16
Y	JOURNAL OF THE CHEMICAL SOCIETY, issued September 1963, W.A.P. Black, et al., "Polymer-ization of Unsaturated Derivatives of 1,2:5,6-Di-O-isopropylidene-D-glucofuranose", pages 4433-4439, entire document.	1-16

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be part of particular relevance

E earlier document published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T

later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X

document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y

document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

G

document member of the same patent family

Date of the actual completion of the international search

18 MARCH 1994

Date of mailing of the international search report

04 APR 1994

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. NOT APPLICABLE

Authorized officer

EVERETT WHITE

Telephone No. (703) 308-0196

Julie Warden for

Form PCT/ISA/210 (second sheet)(July 1992)*

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.